

CLIENT: SABIC INNOVATIVE PLASTICS

1 Structured Products Drive
Long Sault, ON K0C 1P0
Canada

Test Report No: RJ4335-11

Date: November 6, 2015

SAMPLE ID: The following test material was identified as 10 mm multiwall polycarbonate sheet. Five specimens were cut parallel to the ribs and five were cut perpendicular to the ribs.
The various old and new brand names are listed on page 2.

DATE OF RECEIPT: Samples were received on October 21, 2015.

TESTING PERIOD: November 6, 2015.

AUTHORIZATION: Testing authorized by Herb Hummel.

TEST REQUESTED: ASTM Designation D635-10 "Standard Test Method for Rate of Burning and/or Extent and Time of Burning of Plastics in a Horizontal Position".

TEST RESULTS: Detailed test results are presented in the subsequent pages of this report


CLASSIFICATION: The submitted sample is classified CC1 in accordance with UBC Standard 26-7, SEC. 26.706.5
See classification requirements on page 2.

Prepared By



Brian Ortega
Test Technician

**Signed for and on behalf of
QAI Laboratories, Inc.**



Greg Banasky
Senior Technician

Page 1 of 2

THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.

TEST RESULTS:

Number of Specimens Tested: 10
Average Specimen Thickness: 10 mm

OBSERVATIONS: None specimens burned to the 25 mm mark.

CLASSIFICATION REQUIREMENTS PER UBC STANDARD 26-7, SEC. 26.706.5

CC1: Plastic materials which have a burning extent of 1 inch (25mm) or less when tested in nominal .060-inch (1.5mm) thickness (or in the thickness intended for use) by this test.

CC2: Plastic materials which have a burning rate of 2.5 inches per minute (64mm/min) or less when tested in nominal 0.060-inch (1.5mm) thickness (or in the thickness intended for use) by this test.

Old and New Brand Names

Product 4: 10 mm Multiwall Sheet

Old	New
LC21017	LL1UV102R17
LTD2R10	T15DG102R17
LTT2R10	TC2UV102R17
LC15210	T151UV102R17
LTC2R10	TC1UV102R17
LT15210	T152UV102R17
LD21017	TCDG102R17
VT31017	VC2UV103T17
VC31017	VC1UV103T17
VD31017	VCDG103T17
VT15310	V152UV103T17
VC15310	V151UV103T17
VD15310	V15DG103T17
VUH1020	VCUF102R20