



Impact Resistance Test

Date: 2024-09-23
Applicant: POLYROOF SAC
Address: Calle Eucaliptos del Sector Santa Genoveva,
Tax Id: 20553429201
Sample: TK9 1.50mm white, TK9 2.00 mm white
Test: Impact Resistance
Test Conditions: Ambient temperature, relative humidity 65%, and 77° Farenheit

Results

Test Method	Profile	Thickness (mm)	Temperature (F)	Result	
				Joules	ft-lib
ASTM D5628 - 18	TK9 Ag	1.50	70	13.8 (+- 1.3)	10.17
			14	6.50	4.79
		2.00	70	15.6 (+-0.9)	11.51
			14	9.90	7.30



Patricio Rubio
GERENTE DE PROYECTOS

Celular: (+51) 922 242 447

Fijo: (511) 713-4713

Dirección: Calle Eucaliptos del Sector Santa Genoveva,
Lote 1 - C2 - Sub lote B-1, Nave 6. LURIN. LIMA - PERÚ

Website: www.klar.com.pe

www.klar.com.pe